

Material ref, AR310

Black Commercial Fine Ribbed Matting

Material Reference-	310
Colour-	Black
To Specification-	Commercial Fine Ribbed Matting

Basic Properties	Value	Test Method	Unit
Base Polymer Type	NR/SBR		
Indentation Hardness	Not Specified	None	Degrees
Specific Gravity	1.5 +/- 0.05	ASTM D792	g/cm3
Tensile Strength - Minimum	2.8	ASTM D412	Mpa
Elongation @ Break - Minimum	250	ASTM D412	%
Minimum Continuous Working Temperature	-20		°C
Maximum Continuous Working Temperature	70		°C
Maximum Intermittent Working Temperature	90		°C
Compression Set 70 Degrees 22 Hours	35% Max	ASTM D395 Method B	

Other information

Food Use Suitability	Not Recommended
Abrasion Resistance	Moderate
Ozone Weather Resistance	Not Recommended
Flame Retardency	Not Recommended
Electrical Resistance	Not Recommended
General Purpose	Excellent
Issue Date:	May 2010

Data has been copied from manufactures/distributors data test sheet and is intended to be used for guidance and come without warranty or guarantee.

As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline

It is the responsibility of you, the customer to assess the suitability of product supplied for the purpose for which it is to be used.

Datasheet is subject to alteration without prior notice. This Data Sheet supersedes all previous data sheets
Rubberonline Terms and conditions apply

(Source ref: 13-01-03)