

# Material ref AR460

## Tan Natural Shotblast 45° Shore

Material Reference- 460  
Colour- Tan  
To Specification- Abrasion Resistant

<b>Basic Properties</b>	<b>Value</b>	<b>Unit</b>
Base Polymer Type	Natural Rubber	
Indentation Hardness	45 Shore A +/- 5°	Degrees
Specific Gravity	1.1	g/cm3
Tensile Strength - Minimum	14.5 min	Mpa
Elongation @ Break - Minimum	550	%
Tear Strength	20	N/mm
Abrasion	110	MM3
Minimum Continuous Working Temperature	-40	°C
Maximum Continuous Working Temperature	70	°C
Compression Set	35	%

### Other information

Food Use Suitability: Not Recommended  
Abrasion Resistance: Excellent  
Ozone Weather Resistance: Not Recommended  
Electrical Resistance: Not Recommended  
Issue Date: Jan 2012

*Data has been copied from manufactures/distributors data test sheet and is intended to be used for guidance and come without warranty or guarantee.*

*As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline*

*It is the responsibility of you, the customer to assess the suitability of product supplied for the purpose for which it is to be used.*

*Data sheet is subject to alteration without prior notice. This data sheet supersedes all previous data sheets*

*Rubberonline Terms and conditions apply*

(Source ref: 10-16)